

ACRIL-M Y 62

Characteristics of Emulsion

Appearance	: Slightly Opalescent Liquid
Nature	: Polyacrylate Dispersion
Solid Content	: 30 ± 1%
pH (10% Sol.)	: 6.5 ± 0.5
Density	: 1.02
Charge	: Anionic
Mechanical Stability	: Good
Reaction with Ammonia	: Slight Thickening

Characteristics of Film

Appearance	: Clear and Transparent
Elasticity	: Medium-hard
Sticking Level	: None
Light Fastness	: Excellent
Cold-crack Resistance	: Medium

REACH COMPLIANT



Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed & stored.
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non Flammable

Avoid direct contact with skin



Prevent from freezing

Use Gloves / Ensure Ventilation



Acrylic Co-Polymer, medium soft emulsion resin for surface Impregnation of corrected grain leathers to Improve break - especially shoe upper leather.

ACRIL-M Y 62 is a fine particle sized aqueous impregnating resin designed for shoe uppers, particularly corrected type where resistance to acetone and toluene is desired. It gives good filling properties and a smooth pull up during lasting. The leathers achieve a mellow handle, improved scuff resistance with excellent grain break properties.

ACRIL-M Y 62 while applying has to be mixed with a suitable penetrator like Luber 205 or Luber 150. It may also be used in a small quantity in base coat applications for promoting the adhesion of finish.

Usage

- Impregnation : 350 parts Acril-m Y 62
50 parts Luber 205 / Luber 150
600 parts Water
- Impregnation : 200 parts Acril-m Y 62
100 parts Acril-m Y 93
50 parts Luber 205 / Luber 150
650 parts Water
- Base Coat : 100 parts Pigment - Nano Series
100 parts Acril-m X 858
100 parts Acril-m X 79/60
50 parts Acril-m Y 62
50 parts Filler WTD
50 parts Filler 12/61
20 parts Luber 205
530 parts Water

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.