

## FINISH M 15

### Characteristics of Emulsion

Appearance	: Milky White Fluid
Solid Content	: $7 \pm 1\%$
pH (10% Sol.)	: $7.0 \pm 0.5$
Flexibility	: Excellent
Charge	: Anionic
Light fastness	: Excellent

### REACH COMPLIANT



### Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed & stored.  
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



Store in dry place

Use Gloves / Ensure Ventilation



*FINISH M 15 is a handle modifier of mild intensity, water dilutable silliconic dispersion for finer adjustments of feel.*

FINISH M 15 is used in aqueous top coats to improve the handle and provide a soft, natural and slippery feel. It is highly versatile and works for a wide range of leathers from soft uppers to garment leathers. It is non yellowing and promotes abrasion and scuff resistance.

FINISH M 15 is also used to lubricate glazing finishes and provide anti tack surface and improve piling. It is also extremely beneficial to moderate the behaviour of other handle modifiers due to its milder effect. It works well in conjunction with Hicalac 316 or Aquasol 100 to confer the benefit of smooth silky handle. It should not be used with solvent top coats like Top 46, Matt Top, etc.

### Usage

With Top Coats	:	100	parts	Hicalac 316
		50-100	parts	Water
		5-10	parts	Finish M 15
Separate Spray Coat	:	5-10	parts	Finish M 15
		85-90	parts	Water
		150	parts	Finish M 15
	100	parts	Modifier CA/2	
	750	parts	Water	

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.