

GLAZE TOP LM 58

Characteristics of Emulsion

Appearance	: Straw like (can change the color)
Basic Ingredients	: Casein
Solid Content	: 10 ± 1%
pH (10% Sol.)	: 8.5 ± 0.5
Nature	: Hard Protein
Film Appearance	: Transparent, bright
Charge	: Anionic

Hard protein binder suitable for glossy top coat for plated and glazed finishes.

GLAZE TOP LM 58 is ideally suited for use as final top coat in glazed finishes or final glossy polish. It gives leather a silky touch and bright appearance. It also improves resistance to acetone and allows plating at higher temperatures.

GLAZE TOP LM 58 may also be incorporated in resin finish to reduce the tack and improve gloss, dry & wet rub-fastness and print retention. It can be fixed in the usual manner with fixatives like formaline or crosslinkers.

Usage

Stir before use

Glaze Finish (Top Coat)	:	150 parts	Glaze Top LM 58
		50 parts	Protop 18
		3 parts	Xama 7
		750 parts	Water
Glaze Finish (Season Coat)	:	30 parts	Glaze Top LM 58
		970 parts	Normal Season Mixture
Resin Finish	:	40-60 parts	Glaze Top LM 58
		950 parts	Normal Season Mixture

REACH COMPLIANT



Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed & stored.
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



Prevent from freezing

Use Gloves / Ensure Ventilation



Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.