

NOUVOL PK

| Characteristics | | |
|-----------------|-----------------------------|--|
| Composition | : Low Mol. Weight Synthetic | |
| | Phosphoric Ester | |
| Appearance | : Clear, Light Colored Oil | |
| Active Content | : 52 ± 1% | |
| pH (1:10) | : 7.5 ± 0.5 | |
| Emulsions | ; Finely Dispersed | |
| Stability | ; Good | |
| Light Fastness | ; Good | |
| | | |

Suggested Application

- ✓ Cow Nappa
- √ Sheep Nappa
- ✓ Cow softy
- √ Pigskins

REACH COMPLIANT



Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 'c to 35 'c in original pack, well-sealed & stored, Shelf-life : Product is stable for 6 months from the date of production / Invoice,



Non flammable

Avoid direct contact with skin





Prevent from freezing

Use Gloves / Ensure Ventilation



Multifunctional, highly dispersing phosphoric ester with great penetration and crosslinkage to fibre. Produces leather having a very soft touch with light handle.

NOUVOL PK is a highly dispersing fatliquor whose emulsifying part is highly efficient and powerful for dispersing fats making it ideal for pigskins, sheepskins or other leathers containing high natural fats. It provides great penetration and fixability and is not easily extractable as it cross links with leather fibre.

NOUVOL PK gives to the leather a very soft and light touch. Its dispersing power increases the stability of fatliquor emulsion in hard water. When combined with Nouvol SV, it gives uniform softness and touch to all parts of the leather. These features make Nouvol PK a product that can be used for many types of leathers if it is properly combined with other fatliquors.

Usage

To the required quantity of Nouvol PK, add slowly three times of its own weight of water at 60° C, while stirring constantly.

| - Cow Nappa | Fatliquoring | 6.0% Nouvol PK 4.0% Nouvol LS 55 3.0% Maradol C 6.0% Lubotop AM |
|---------------|--------------|--|
| ■ Sheep Nappa | Faliquoring | 6.0% Nouvol PK 4.0% Nouvol LS 55 2.0% Luber SAS 1.0% Maradol C |
| Cow Softy | Fatliquoring | 2.0% Nouvol PK 2.0% Luber SN 2.0% Luber G 60 2.0% Maradol C |

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.