

UREZ 785 M

Characteristics of Emulsion

Appearance	: Milky Emulsion
Nature	: Aliphatic Polyurethane Dispersion
Charge	: Anionic
Solid Content	: 22 ± 1%
pH (10% Sol.)	: 9.0 ± 0.5
N.M.P./ NEP Content (%)	: Nil
Mechanical Stability	: Good

Characteristics of Film

Appearance	: Opaque and Matt
Gloss	: 6 BYK Gardner
Shore A Hardness	: 95 (Zwick/Roell)
Light Fastness	: Excellent
Cold-crack Resistance	: Excellent

REACH COMPLIANT



Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °C to 35 °C in original pack, well-sealed & stored.
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



IMPORTANT: PROTECT FROM FREEZING.

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.

Matt Polyurethane Dispersion for use as aqueous top coat for an elegant look and VOC free finishes on leather.

UREZ 785 M is a dull waterborne aliphatic polyurethane dispersion designed for high performance upper and upholstery leather. Treated leathers will have a pleasant, soft and warm handle that fulfils high standards of fastness. The film properties confer good flexibility, excellent rub fastness, perspiration and ageing resistance.

UREZ 785 M can be combined with Urez 785 G for regulating the final gloss on leather. The product can be blended with various feel modifiers to achieve the desired touch. It can be cross-linked with the help of Xama 2 or Xama 7.

Usage

- Matt Top Coat : 900 parts Urez 785 M
85 parts Glaze Top N
7 parts Finish M 45
3 parts Leveller 168
5 parts Xama 7
- Low Gloss Top Coat : 500 parts Urez 785 M
495 parts Urez 785 G
5 parts Xama 7



Store in dry place

Use Gloves / Ensure Ventilation

