

ACRIL-M KT 35

ACRIL-M KT 35 is a soft acrylic binder specially designed for the use in cationic finishing system for leather where it can partly replace polyurethane as main binder.

CHARACTERISTICS OF EMULSION

Appearance	: Milky White
Solid Content	: 35 ± 1%
pH (10% Sol.)	: 2.5 ± 0.5
Nature	: Cationic
Mechanical Stability	: Good

CHARACTERISTICS OF FILM

Elongation	: 10 (1 Min. - 10 Max.)
Gloss	: 07 (1 Matt - 10 Glossy)
Shore Hardness	: 02 (1 Softest - 10 Hardest)
Anchorage	: Good
Light Fastness	: Excellent
Cold-crack Resistance	: Good

· **ACRIL-M KT 35** is a soft acrylic binder for the use in cationic finishing of leather. It imparts a soft and stretchy finish to the leather. It can be combined with PUD 48 KT or PUD 40 KT to achieve particular results. It has very good anchorage to the leather and provides good feel without excessive loading of the grain.

Gloss and other physical properties of the finish conferred by **ACRIL-M KT 35** can be improved by adding Xama-7 in the season.

SUGGESTED APPLICATIONS:

Polishing Ground	:	20 parts Black NA	
		50 parts Novocat Black R	
		100 parts Brillento 91 KT	
		60 parts Filler KT	
		700 parts Water	
		30 parts ACRIL-M KT 35	1 to 2 X coats,
	40 parts PUD 48 KT	dry well, Polish.	
Season Coat	:	10 parts Black NA	
		30 parts Novocat Black R	
		100 parts Brillento 91 KT	
		50 parts Celina 34 KT	
		660 parts Water	
		75 parts ACRIL-M KT 35	2 to 3 X coats,
	75 parts PUD 40 KT	dry well, Finiflex.	

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.