

## **NEOPHOL HMK**

Characteristics	
Composition	: Synthetic Phosphated
	Polymers & Natural
	Phospholipds
Appearance	: Cream / Yellowish Thick
	Paste
Active Content	: 40 ± 1%
pH (1:10)	: 7.5 ± 0.5
Solubility	: Soluble in water

## Suggested Application

- ✓ Chrome Free
- ✓ Upholstery
- ✓ Industrial Glovina
- ✓ Lining
- ✓ Shoe softie

REACH COMPLIANT



Green-Trek-Compliant A symbol of our commitment to sustainable technologies

Store between +5 'c to 35 'c in original pack, well-sealed & stored. Product is stable for 24 months from the date of production / Invoice.



Non flammable Avoid direct contact with skin





Store in dry place Use Gloves / Ensure Ventilation



## NEOPHOL HMK

Fibre relaxing polymeric softening agents for flat grained leathers. Penetrates deep for excellent softness, has a fluffy handle and pleasant touch.

**NEOPHOL HMK** is used for soft articles like furniture leather and industrial alovina. It can be used as main fatliauor or in combination with regular fatliquors. It reduces fibre tension, relaxes the leather giving it warm deep softness, evenness in milling and a wrinkle-free appearance with clean and bright white surfaces.

One of the unique property of **Neophol HMK** is that it shows low COD and BOD- because it contains no diluents and solvents like conventional high solid fatliquors. Its extremely powerful and efficient ingredients penetrate well, ensuring no wastage of active components in the exhaust.

**NEOPHOL HMK** in combination with Repallon ESW gives more silky feel on leather. When combined with Neophol CX, it gives a deep softness required for gloving leathers.

## Usage

To the required quantity of **HMK** add slowly, three times of its own weight of water at 60°C, while stirring.

Buff Upholstery 12-14% **NEOPHOL HMK** 

3-5% Uphol PFK

12-15% **NEOPHOL HMK** Industrial Gloving

> 3-5% Repallon ESW 2-3% Neophol CX

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.